

The only adhesive line developed exclusively for fiber optics

ANAEBOND™ #101
ANAEROBIC Adhesive for Fiber Optic Bonding
Description:

ANAEBOND™ 101 is a single component anaerobic retaining adhesive that develops high strength rapidly when confined in the absence of air between close fitting metal parts. Glass, ceramic or plastic surfaces may be bonded with the use of AnaeBond™ PRIMER #1. It has high temperature resistance properties, it is particularly useful for bonding cylindrical fitting parts where strength at high temperatures is required. Applications include termination of fiber optic connectors; holding gears and sprockets onto gearbox shafts and rotors on electric motor shafts.

Physical Properties:

Chemical Type	Urethane methacrylate	
Appearance	Green, fluorescent liquid	
Specific gravity	1.13 @ 25°C	
	Typical	
	Value	Range
Viscosity @ 25°C, mPa.s(cP)		
Brookfield RVT		
Spindle 2 @ 20 rpm	500	400-600
DIN 54453, MV		
D=129's after t=180 secs	450	300-600
Flash Point (COC), °C	>100	

Recommended Usage Temperatures:

Storage:	-5 to 30°C	(23 to 86°F)
Installation:	0 to 38°C	(32 to 100°F)
Operating:	-40 to 75°C	(-40 to 167°F)

Storage:

Product is properly stored in a cool, dry location in unopened containers at a temperature between 8°C and 28°C (46°F to 82°F) unless otherwise labeled. Optional storage is at the lower end of this temperature range. To prevent contamination of unused product, do not return any material to its original container

ANGSTRÖMBOND® is a REGISTERED TRADEMARK of Fiber Optic Center, Inc., New Bedford MA, USA

Fiber Optic Center™, Inc. MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS OR OTHERWISE, with respect to its products. In addition, while the information herein is believed to be reliable, no warranty is expressed or implied regarding the accuracy of the data or the results to be obtained from the use thereof. All recommendations or suggestion for use are made without guarantee -- inasmuch as conditions of use are beyond our control. The properties given are typical values, and are not intended for use in preparing specifications. Users should make their own test to determine the suitability of this product for their own purposes.

Rev. C 6/2001